Effect of Ar Plasma Treatment for Surface of Insert Metal on Property of TLP Bonding Joint for Power Module

삽입금속 표면 Ar 플라즈마 처리가 전력모듈을 위한 TLP 접합부 특성에 미치는 영향

Seungju Baek^{*,**}, Dong-Yurl Yu^{*,***}, Jun-Hyuk Son^{*,***}, Junghwan Bang^{*}, Jungsoo Kim^{*},
Min-Su Kim^{*}, Han-Bo-Ram Lee^{**} and Yong-Ho Ko^{*,****,†}

^{*}Advanced Functional Technology R&D Department, Korea Institute of Industrial Technology (KITECH),
Incheon, 21999, Korea

^{**}Department of Materials Science and Engineering, Incheon National University, Incheon, 22012, Korea

^{***}Department of Material Science and Engineering, Korea University, Seoul, 02841, Korea

^{****}Industrial Materials and Smart Manufacturing Engineering, University of Science and Technology
(UST), Daejeon, 34113, Korea

[†]Corresponding author : yonghoko@kitech.re.kr

(Received ; June 24, 2020 ; Revised July 3, 2020 ; Accepted August 7, 2020)

Abstract

In this study, we investigated the effect of plasma treatment for the surface of an insert bonding metal on the properties of a transient liquid phase (TLP) bonding joint for a power module. Sn preforms, as the insert bonding metal for the TLP bonding, were used with and without Ar plasma treatment. To investigate the effect of Ar plasma treatment, the TLP bonding for two structures of Cu-finished Si chip/Sn preform/organic solderability preservative (OSP)-finished direct bond copper (DBC) substrate (Cu/Sn/Cu), and Ni-finished Si chip/Sn preform/Ni(P)-finished DBC substrate (Ni/Sn/Ni) was performed with 1 MPa at 300 °C and the bonding times were 10, 30, and 60 min, respectively. After the TLP bonding, we observed interfacial reactions and formations of intermetallic compounds (IMCs) under various bonding conditions. To evaluate mechanical properties, a shear test was also performed. Compared to the TLP bonding joint that used bare Sn preforms without Ar plasma treatment, growth of IMCs at the bonding joint that used Sn preforms with Ar plasma treatment occurred faster, and the IMCs could be formed through the entire joint despite the bonding time of 10 min. Meanwhile, by increasing the bonding time, Cu₆Sn₅ and Cu₃Sn were formed at the Cu/Sn/Cu TLP bonding joint, whereas Ni₃Sn₄, Ni-Sn-P, and Ni₃P were observed at the Ni/Sn/Ni joint. In the case of the Cu/Sn/Cu joint, we observed that increasing Cu₃Sn formation while increasing the bonding time could be beneficial to the shear strength of the joint. Further, shear strengths of the joint were not significantly changed under the bonding conditions after Ni₃Sn₄, Ni-Sn-P, and Ni₃P IMCs were formed at the entire joint of the Ni/Sn/Ni.

Key Words : Transient liquid phase (TLP) bonding, Power module, Interfacial reaction, Intermetallic compound (IMC), Shear test

1. Introduction

The power module, which serves to convert, transform, distribute, and control electrical energy, is a core component of inverters and converters in fields such as

renewable energy, automobiles, and railways¹⁾. The power module consists of a power semiconductor chip, substrate, Al or Cu wire for electrical connection, base plate, etc., and functions as a module through the bonding of each component. The use of power modules has been gradually expanding recently, and eco-friendly ve-

hicles such as pure electrical vehicles (EVs) and hybrid electrical vehicles (HEVs) are being increasingly used²⁾. Si, SiC, and GaN-based devices are used for the power semiconductor chip constituting the power module³⁾, and ceramic-based substrates such as direct bond copper (DBC) and active metal brazing (AMB) are used for the substrate through various surface treatments⁴⁾.

For the bond between the power semiconductor chip and substrate, a soldering technology using solders containing Pb has been used for some time. However, as recent environmental regulations have prohibited the use of Pb, Sn-based lead-free solders (e.g., Sn-Ag-Cu, Sn-Zn) have primarily been used⁵⁾. As power modules used in automobiles are generally exposed to high-temperature environments of 200 °C or more, when applying the soldering method using lead-free solders based on Sn with a melting point of approximately 231 °C, reliability-related issues such as a re-melting phenomenon can occur during using the power module after bonding the chip and substrate⁶⁾. To address this problem, many bonding methods are studied for applying to power module using bonding materials and bonding processes applicable in high-temperature environments. In this regard, a soldering method using an Au-Sn lead-free solder with a high melting point^{7,8)} and a sintering method using pastes of Ag or Cu metal powders are being studied^{9,10)}. However, the Au-Sn lead-free solder is difficult to industrially apply due to the high price of Au¹¹⁾. Regarding the sintering method using a metal powder such as Ag as a bonding material, though it has the advantage of improved characteristics with finer particles, material costs also increase with finer particles¹²⁾. Furthermore, when using a Cu metal powder, it is difficult to solve the oxidation problem of the Cu material itself^{10,12)}. Accordingly, a transient liquid phase (TLP) bonding technology has been recently proposed to improve on the disadvantages of the soldering and sintering bonding methods¹³⁾.

TLP bonding forms intermetallic compounds (IMCs) at the bonding joint, which form through the diffusion of metal atoms at relatively low temperatures, while melting the low-melting-point insert metal that acts as a bonding material between the high-melting-point material¹³⁾. The IMCs formed throughout the entire bonding joint can secure reliability even in high-temperature environments due to their high melting point. However, researchers have noted that one major disadvantage of TLP bonding is that long process times are required to form the entire bonding joint through uniform IMCs¹¹⁾.

This study reported on the IMC formation and growth of a TLP bonding joint according to the TLP bonding time through plasma pretreatment on a metal bonding

material inserted for bonding. A metal foil Sn preform was used as the bonding material and the influences of Ar plasma treatment on the interfacial reaction of the TLP bonding joint, IMC formation, and mechanical properties through Ar plasma treatment on the surface of Sn preform were investigated.

2. Experimental Method

Si chips and DBC substrates were used for TLP bonding. For the Si chip, Ti and Cu were deposited to 0.05 and 0.5 μm on the Si wafer via sputtering, respectively. To then compare the properties of the TLP bonding joint according to different final surface-finished materials of the chip, Cu and Ni were separately deposited to fabricate two types of Si wafers. The Cu and Ni were finally deposited to a thickness of 10 μm using the electroplating method. The Si wafer on which the Cu and Ni were finally deposited was diced into a size of 4 mm × 4 mm and used as the chip for TLP bonding. For the substrate used for bonding, DBC substrates in which 300 μm of Cu was stacked on the upper and lower surfaces of a 380 μm Al₂O₃-based ceramic substrate were used. This DBC substrate was 17.8 mm × 12.7 mm × 0.98 mm in size. To compare the bonding joint properties according to the surface-finished materials, two types of DBC substrates were also fabricated. One was the DBC substrate finished with organic solderability preservative (OSP) of several nm and the other was the DBC substrate treated with Ni(P) of approximately 5 μm. Meanwhile, for the TLP bonding material, we a Sn preform with a size of 4 mm × 4 mm and thickness of approximately 40 μm. To investigate the influence of Ar plasma treatment on the TLP bonding joint, Ar plasma pretreatment on the upper and lower surfaces of the Sn preform was performed. The Ar plasma surface treatment was conducted for approximately 10 minutes at a gas flow of 100 sccm, a power of 100 W, and a vacuum degree of 0.5 torr. To perform TLP bonding, the Sn preform was first placed on the DBC substrate and the chip was placed on the Sn preform. After placing, the TLP bonding was performed using a chamber capable of controlling the temperature and pressure in a vacuum state. Two samples with TLP bonding were fabricated: a Cu surface-treated Si chip/Sn preform/OSP surface-finished DBC (Cu/Sn/Cu) structure, and a Ni surface-treated Si Chip/Sn preform/Ni(P) surface-finished DBC (Ni/Sn/Ni) structure. After the TLP bonding, properties of the bonding joint were compared and evaluated according to the TLP bonding joint structure. TLP bonding was performed by applying a pressure of 1 MPa in a vacuum chamber at 300 °C, and the proper-

Fig. 1 Schematic diagrams of TLP bonding process for (a) Cu/Sn/Cu and (b) Ni/Sn/Ni

ties of the TLP bonding joints according to bonding time were compared for three bonding time conditions (10, 30, and 60 minutes). Fig. 1 shows a schematic diagram of the Cu/Sn/Cu and Ni/Sn/Ni TLP bonding process.

Meanwhile, after TLP bonding, to analyze the structure of the bonding joint, the bonding time, and the interfacial reaction according to the Ar plasma treatment and the cross-section of the specimen was polished and then scanning electron microscopy (SEM, Inspect F, FEI, USA) and energy-dispersive X-ray spectroscopy (EDS) were used to observe and analyze the bonding joint. Moreover, to evaluate the mechanical properties of the TLP bonding joint, a shear tester (DAGE-4000, Nordson DAGE, UK) was also used to compare and evaluate the bonding strength according to each bonding condition. The bonding strength evaluation was performed at a shear height of 25 μm and a shear speed of 200 $\mu\text{m/s}$. Further, after evaluating the shear strength, cross-sectional analyses were performed on the fractured loci using SEM and EDS for the bonding joints structure, the bonding time, and the effects of Ar plasma surface treatment were compared.

3. Experimental Results and Discussion

Fig. 2 shows the SEM micrographs of the cross-sectional analysis after Cu/Sn/Cu TLP bonding. According to the cross-sectional analysis at 10 minutes of bonding time, the IMCs formed in the bonding joint consisted of Cu_6Sn_5 and Cu_3Sn IMCs, which are known¹³⁾ to typi-

Fig. 2 Cross-sectional SEM micrographs of Cu/Sn/Cu joints with various bonding times

cally form in the Cu-Sn system. In addition, when using the Sn preform not applied to Ar plasma surface treatment, residual Sn was remained after forming the IMCs at the bonding joint. Conversely, in the bonding joint using the Ar plasma surface-treated Sn preform, IMCs formed throughout the entire bonding joint from 10 minutes of the bonding time. When the bonding time was increased to 30 or 60 minutes, IMCs formed throughout the entire bonding joint regardless of Ar plasma surface treatment. Fig. 3 shows the ratio of IMC types forming the Cu/Sn/Cu TLP bonding joint according to the bonding time and Ar plasma treatment.

Fig. 3 Ratio of IMC formed at Cu/Sn/Cu joints with (Ar(Cu)) and without (Cu) plasma surface treatment

Regardless of Ar plasma treatment, as the bonding time increased, the ratio of Cu_6Sn_5 decreased and the ratio of Cu_3Sn increased. Regarding the IMCs formed in the Cu-Sn system, Cu_6Sn_5 first forms by the diffusion reaction of Cu and Sn. Afterwards, Cu_3Sn is known to form between Cu_6Sn_5 and Cu due to the diffusion of additional Cu^[14]. Therefore, Cu_6Sn_5 grew at the initial Cu/Sn/Cu bonding joint and Cu_3Sn grew at the Cu_6Sn_5 /Cu interface as the bonding time increased. Meanwhile, when using the Ar plasma surface-treated Sn preform for bonding at bonding times of 10, 30, and 60 minutes (Ar(Cu)-10, 30, 60), the ratio of Cu_3Sn at the bonding joint at all bonding times exceeded that in the bonding joint formed without plasma treatment at 10, 30, and 60 minutes of bonding time (Cu-10, 30, 60). When using Ar of a representative inert gas as the plasma reaction gas, Ar plasma surface treatment was performed on the Sn preform to utilize the advantages of physical organic material removal and surface activation^[15] rather than chemical reactions with the sample surface. In this regard, it is assumed that Ar plasma treatment could enhance the wettability, reactivity, and bonding characteristics at the interface, which result in forming uniform IMCs at the TLP bonding joint and leading to a high growth rate of Cu_3Sn due to continuously accelerate Cu diffusion. Fig. 4 shows the bonding strength according to plasma surface treatment and bonding time of the Cu/Sn/Cu TLP bonding joint. When plasma surface treatment was not applied, the bonding strength was ap-

Fig. 4 Shear strength of Cu/Sn/Cu joints for various bonding times and Ar plasma treatment

proximately 48 MPa at a bonding time of 10 minutes (Cu-10) and a relatively higher value than the other conditions. In the bonding joint without plasma treatment at a bonding time of 30 minutes (Cu-30), the bonding strength was 24 MPa, and in that with Ar plasma treatment (Ar(Cu)-30), the bonding strength was 29 MPa. When the bonding time was increased to 60 minutes, regardless of plasma treatment (Cu-60, Ar(Cu)-60), the bonding strength tended to be increased with bonding strengths of 25 and 34 MPa, respectively. After 30 minutes of bonding time, a relatively high strength was measured when plasma treatment was applied. Fig. 5

Fig. 5 (a) Cross sectional SEM micrographs of fracture surface and (b) fracture mode of Cu/Sn/Cu joints after shear test

shows the SEM micrographs of the cross-sectioned fracture loci after evaluating the bonding strength of the Cu/Sn/Cu TLP bonding joint, as well as a fracture diagram based on the SEM results. The results demonstrated that, regardless of the bonding time or surface treatment, fracture occurred on the substrate-side, which was the bottom of the bonding joint. As shown in Fig. 5 (a) and (b) Case 1, fracture of the bonding time of 10 minutes without plasma surface treatment occurred at the interface of the residual Sn and IMC and the interface between the Cu_6Sn_5 and Cu_3Sn IMCs at the bonding joint. Above mentioned, the shear strength for the 10 minutes of bonding time without surface treatment was relatively high strength. From the cross-sectional analysis of the fracture loci, it was assumed that this was attributed to the ductility characteristics which were shown at Sn-based solder bonding joints due to the influence of remained Sn after the formation of IMCs at the initial bonding joint. Thus, at the initial bonding process time, when residual Sn remained in the bonding joint, the bonding strength showed a similar trend to previous research showing high bonding strength values¹³⁾. Meanwhile, in the case of 10 minutes of bonding time with plasma surface treatment, as shown in Fig. 5 (a) and (b) Case 2, fracture occurred at the interface of Cu_6Sn_5 and Cu_3Sn . This differed from the case in which Ar plasma treatment was not applied because the IMCs formed throughout the entire bonding joint from a bonding time of 10 minutes when Ar plasma surface treatment was applied. Therefore, the bonding strength for 10 minutes of bonding time with Ar plasma surface treatment was lower than that without Ar plasma surface treatment due to the fracture at the IMC interfaces because of IMCs which were formed at the whole bonding joint. As shown in Fig. 5 (a) and Fig. 5 (b) Case 3 and 4, bonding joint fractures occurred in the Cu_6Sn_5 IMC layer and the interface between Cu_6Sn_5 and Cu_3Sn when the bonding times were increased to 30 and 60 minutes, regardless of plasma treatment. As mentioned in Fig. 3, the ratio of Cu_3Sn IMCs at the bonding joint increased as the bonding time increased. Although the fracture loci were similar to each other after 30 minutes of bonding time, the increase in strength as the bonding time increased was influenced by the increase in the ratio of Cu_3Sn IMCs at the bonding joint. Cu_3Sn generally has a higher mechanical properties such as Young's modulus etc. than Cu_6Sn_5 ¹⁶⁾. In this study, when the bonding time increased and Ar plasma surface treatment was applied, the ratio of Cu_3Sn increased, which result in influencing on the increase in strength of the TLP bonding joint.

Fig. 6 shows the SEM micrographs of the cross-sectioned joints after Ni/Sn/Ni TLP bonding. The IMCs

Fig. 6 Cross-sectional SEM micrographs of Ni/Sn/Ni joints with various bonding times

formed at the bonding joint were Ni_3Sn_4 . When Ar plasma surface treatment was not applied, residual Sn was observed in the middle of the bonding joint for the bonding time of 10 minutes as in the Cu/Sn/Cu bonding joint. On the other hand, when using the Ar plasma surface-treated Sn preform, IMCs formed throughout the entire bonding joint. It is known that Ni_3Sn_4 IMCs are formed in the Ni-Sn system¹³⁾, and Ni-Sn-P and Ni_3P are also known to form at the interface between Sn-based solders and electroless Ni(P) ¹⁷⁻²⁰⁾. Similar to a previous research, in this study, Ni-Sn-P and Ni_3P were also observed at the interface between the Ni(P) surface-finished DBC substrate and Sn preform. Meanwhile, as the bonding time increased to 30 and 60 minutes, Ni_3Sn_4 IMCs formed throughout the entire bonding joint even without Ar plasma surface treatment. Fig. 7 shows the ratio of IMCs formed at the bonding joint for various conditions of Ar plasma surface treatment and bonding time. In the case of 10 minutes of bonding time without Ar plasma surface treatment (Ni-10), Ni_3Sn_4 IMCs had the lowest ratio at the bonding joint due to the influence of residual Sn that could not form IMCs at the bonding joint. However, as the bonding time increased to 30 and 60 minutes (Ni-30 and Ni-60), the residual Sn reacted and ratios of Ni_3Sn_4 , Ni-Sn-P , and Ni_3P were increased. While Ni-Sn-P and Ni_3P partially increased with the bonding time after Ni_3Sn_4 IMCs formed throughout the entire bonding joint, the ratios

Fig. 7 Ratio of IMC formed at Ni/Sn/Ni joints with (Ar(Ni)) and without(Ni) plasma surface treatment

of Ni₃Sn₄, Ni-Sn-P, and Ni₃P were not remarkably increased. Moreover, in the Ar plasma-treated bonding joints, Ni₃Sn₄ IMCs formed throughout the entire bonding joint from a bonding time of 10 minutes (Ni(Ar)-10) and the ratios of IMCs forming the bonding joint were not noticeably changed even as the bonding time increased to 30 and 60 minutes (Ni(Ar)-30, Ni(Ar)-60).

The bonding strengths of the Ni/Sn/Ni TLP bonding joint were showed in Fig. 8 and these results were a similar trend to the bonding strength results of the Cu/Sn/Cu TLP bonding joint. For the bonding joint using an Ar plasma surface-treated Sn preform at a bonding time of 10 minutes (Ni-10), the bonding joint showed a high strength of 43 MPa due to the residual Sn. It was assumed that this was attributed to the ductility characteristics of the residual Sn, as described for the Cu/Sn/Cu TLP bonding joint. However, as the bonding time increased to 30 and 60 minutes (Ni-30, Ni-60), the bonding strength was about 23-25 MPa after Ni₃Sn₄ formed throughout the entire bonding joint and the strength was not greatly changed with increasing the bonding time. Meanwhile, as in the case of Ar plasma surface treatment, Ni₃Sn₄ IMCs formed throughout the entire bonding joint from the bonding time of 10 minutes (Ni(Ar)-10) and the bonding strengths were similar with the initial strength at 10 minutes although the bonding time increased to 30 and 60 minutes (Ni(Ar)-30, Ni(Ar)-60). This means that the Ar plasma surface treatment and the bonding time could not remarkably affect to the bonding strength when Ni₃Sn₄ IMCs form throughout the entire bonding joint in the Ni/Sn/Ni structure. Fig. 9 shows the cross-sectional analysis results of the fracture loci of the Ni/Sn/Ni TLP bonding joint and a schematic diagram of fracture occurrence

Fig. 8 Shear strength of Ni/Sn/Ni joints for various bonding times and Ar plasma treatment

with various conditions of bonding time and plasma surface treatment. Similar to the Cu/Sn/Cu TLP bonding joint, the bonding joint fractures occurred mostly at the substrate-side of the bonding joint. When residual Sn remains at the bonding joint without plasma treatment at the bonding time of 10 minutes, as shown in Fig. 9 (a) and (b) Case 1, the fracture loci occurs at the interface between Ni₃Sn₄ IMC and residual Sn. When the bonding time increased to 30 and 60 minutes, however, fractures occurred at the Ni₃Sn₄ IMC, Ni₃Sn₄, and Ni-Sn-P interfaces due to the formation of Ni₃Sn₄ IMCs throughout the whole joint. In contrast, when Ar plasma treatment was applied as shown in Fig. 9 (a) and (b) Case 2, fractures occurred at the Ni₃Sn₄ IMC, Ni₃Sn₄ and Ni-Sn-P interfaces from a bonding time of 10 minutes. Due to the similarity of the fracture mode, bonding strengths in the bonding joint of 30 minutes bonding time without plasma treatment (Ni-30) and those after 10 minutes bonding time with Ar plasma treatment (Ar(Ni)-10) were similarly measured.

4. Conclusions

As a method to shorten the TLP bonding process time for power modules, we applied Ar plasma treatment to the surface of the Sn preform insert metal used as the bonding material and investigated the effect of Ar plasma treatment on the mechanical properties and interfacial reactions of the TLP bonding joint. In addition, TLP bonding joints with Cu/Sn/Cu and Ni/Sn/Ni structures were formed and investigated the properties of bonding joints with various TLP bonding conditions for Ar plasma treatment, TLP bonding joint structures, and TLP bonding time.

1) When the Sn preform was applied to Ar plasma

Fig. 9 (a) Cross sectional SEM micrographs of fracture surface and (b) fracture mode of Ni/Sn/Ni joints after shear test

treatment, even at a bonding time of 10 minutes, IMCs formed throughout the entire Cu/Sn/Cu and Ni/Sn/Ni bonding joints. It was assumed that the diffusion of metal atoms such as Cu, Ni, and Sn was influenced due to the physical cleaning effect and so on by the Ar plasma treatment.

2) When Ar plasma treatment was not applied, at the bonding time of 10 minutes, IMCs were not fully formed throughout the entire bonding joints of Cu/Sn/Cu and Ni/Sn/Ni structures and residual Sn was observed.

3) Cu_6Sn_5 and Cu_3Sn IMCs formed in the Cu/Sn/Cu TLP bonding joint while Ni_3Sn_4 , Ni-Sn-P, and Ni_3P IMCs were observed in the Ni/Sn/Ni TLP bonding joint.

4) The ratio of Cu_3Sn IMCs in the Cu/Sn/Cu bonding joint increased as the bonding time increased and this affected to increase the strength of the bonding joint.

5) In the Ni/Sn/Ni bonding joint, the Ar plasma surface treatment and the bonding time could not remarkably affect to the bonding strength when Ni_3Sn_4 IMCs were fully formed throughout the entire bonding joint.

6) From these results, when using a preform insert metal as the bonding material for TLP bonding, Ar treatment on the preform is expected to shorten the process time by quickly forming the entire TLP bonding joint through IMCs.

Acknowledgments

This study has been conducted with the support of the

Korea Institute of Industrial Technology as "Development of root technology for multi-product flexible production (kitech EO-20-0015)".

ORCID: Seungju Baek: <https://orcid.org/0000-0003-0746-7378>

ORCID: Yong-Ho Ko: <https://orcid.org/0000-0002-1619-8467>

References

1. M. Thoben, F. Sauerland, K. Mainka, S. Edenharther and L. Beurenaut, Lifetime modeling and simulation of power modules for hybrid electrical/electrical vehicles, *Microelectron. Reliab.* 54 (2014) 1806-1812. <https://doi.org/10.1016/j.microrel.2014.07.009>
2. Y. Wang, S. Jones, A. Dai and G. Liu, Reliability enhancement by integrated liquid cooling in power IGBT modules for hybrid and electric vehicles, *Microelectron. Reliab.* 54 (2014) 1911-1915. <https://doi.org/10.1016/j.microrel.2014.07.037>
3. L. A. Navarro, X. Perpiñà, P. Godignon, J. Montserrat, V. Banu, M. Vellvehi and X. Jordà, Thermomechanical assessment of die-attach materials for wide bandgap semiconductor devices and harsh environment applications, *IEEE Trans. Power Electron.* 29(5) (2014) 2261-2271. <https://doi.org/10.1109/TPEL.2013.2279607>
4. H. A. Mantooth, S. S. Ang, B. L. Rowden and J. C. Balda, Packaging of High-Temperature Power Semiconductor Modules, *ECS Trans.* 27(1) (2010) 909-914.

- <https://doi.org/10.1149/1.3360729>
5. K. Sukanuma, Advances in lead-free electronics soldering, *Curr. Opin. Solid State Mater. Sci.* 5(1) (2001), 55-64.
[https://doi.org/10.1016/S1359-0286\(00\)00036-X](https://doi.org/10.1016/S1359-0286(00)00036-X)
 6. H. Zhang, S. S. Ang, H. A. Mantooth and S. Krishnamurthy, A high temperature, double-sided cooling SiC power electronics module, *IEEE Energy Convers. Congr. Expo. (ECCE)* (2013) 2877-2883.
<https://doi.org/10.1109/ECCE.2013.6647075>
 7. D. G. Ivey, Microstructural characterization of Au/Sn solder for packaging in optoelectronic applications, *Micron*. 29(4) (1998) 281-287.
[https://doi.org/10.1016/S0968-4328\(97\)00057-7](https://doi.org/10.1016/S0968-4328(97)00057-7)
 8. J. W. Yoon, H. S. Chun and S. B. Jung, Liquid-state and solid-state interfacial reactions of fluxless-bonded Au-20Sn/ENIG solder joint, *J. Alloys Compd.* 469 (2009) 108-115.
<https://doi.org/10.1016/j.jallcom.2008.01.077>
 9. B. S. Lee and J. W. Yoon, Die-Attach for Power Devices Using the Ag Sintering Process, Interfacial Microstructure and Mechanical Strength, *Met. Mater. Int.* 23 (2017) 958-963.
<https://doi.org/10.1007/s12540-017-6908-1>
 10. J. W. Yoon, J. H. Back and S. B. Jung, Effect of surface finish metallization on mechanical strength of Ag sintered joint, *Microelectron. Eng.* 198 (2018) 15-21.
<https://doi.org/10.1016/j.mee.2018.06.009>
 11. S. Sohn, B. Moon, J. Lee, N. Kang and Y. Moon, Interlayer Material Design Reducing Transient Liquid Phase Bonding Time, *Electron. Mater.* 16(2) (2020) 106-114.
<https://doi.org/10.1007/s13391-019-00191-2>
 12. J. W. Yoon, S. Bae, B. S. Lee and S. B. Jung, Bonding of power device to ceramic substrate using Sn-coated Cu micro paste for high-temperature applications, *Appl. Surf. Sci.* 515 (2020).
<https://doi.org/10.1016/j.apsusc.2020.146060>
 13. B. S. Lee, S. K. Hyun and J. W. Yoon, Cu-Sn and Ni-Sn transient liquid phase bonding for die-attach technology applications in high-temperature power electronics packaging, *J. Mater. Electron.* 28(11) (2017) 7827-7833.
<https://doi.org/10.1007/s10854-017-6479-4>
 14. X. Liang, X. Li, P. Yao, Y. Li and F. Jin, Interfacial reaction during fabricating of full Cu₃Sn joints in micro-electronic packaging, *Mater. Sci. Tech.* 33(17) (2017) 2024-2031.
<https://doi.org/10.1080/02670836.2017.1342365>
 15. J. Wang, Q. Wang, D. Wang and J. Cai, Study on Ar(5%H₂) Plasma Pretreatment for Cu/Sn/Cu Solid-State-Diffusion Bonding in 3D Interconnection, *Proceedings Electronic Components and Technology Conference (ECTC)*, Las Vegas, NV, USA (2016) 1765-1771.
<https://doi.org/10.1109/ECTC.2016.110>
 16. C. C. Lee, P. J. Wang and J. S. Kim, Are intermetallics in solder joints really brittle?, *Proceedings Electronic Components and Technology Conference (ECTC)*, Reno, NV, USA (2007) 648-652.
<https://doi.org/10.1109/ECTC.2007.373866>
 17. J. W. Yoon and S. B. Jung, Growth kinetics of Ni₃Sn₄ and Ni₃P layer between Sn-3.5Ag solder and electroless Ni-P substrate, *J. Alloys Compd.* 376 (2004) 105-110.
<https://doi.org/10.1016/j.jallcom.2003.12.029>
 18. H. Lee, S. H. hun, G. H. Jung, and S. J. Ham, Effects of the Electroless Ni-P Thickness and Assembly Process on Solder Ball Joint Reliability, *J. Weld. Join.* 32(4) (2014) 60-67.
<https://doi.org/10.5781/JWJ.2014.32.3.60>
 19. J. W. Yoon and S. B. Jung, Coupling effect of Cu-(ENIG)/Sn-Ag-(Cu)/Cu(ENIG) sandwich solder joint, *J. Weld. Join.* 46 (2006) 33-35.
 20. J. H. Back, S. Yoo, D. G. Han, S. B. Jung, and J. W. Yoon, Interfacial Reactions and Mechanical Strength of Sn-3.0Ag-0.5Cu/0.1μm-Ni Thin ENEPIG Solder Joints, *J. Weld. Join.* 35(6) (2017) 51-58.
<https://doi.org/10.5781/JWJ.2017.35.6.8>

삽입금속 표면 Ar 플라즈마 처리가 전력모듈을 위한 TLP 접합부 특성에 미치는 영향

Effect of Ar Plasma Treatment for Surface of Insert Metal on Property of TLP Bonding Joint for Power Module

백승주*,** · 유동열*,*** · 손준혁*,*** · 방정환* · 김정수* · 김민수* · 이한보람** · 고용호*,****,†

*한국생산기술연구원 부품기능연구부

**인천대학교 신소재공학과

***고려대학교 신소재공학과

****과학기술연합대학원대학교 산업소재 · 스마트제조 공학

1. 서 론

최전력모듈 (power module)은 전기에너지의 변환, 변압, 분배, 제어 등의 역할을 수행하는 부품으로 신재생에너지, 자동차, 철도 등의 분야에서 인버터 (inverter)/컨버터 (converter)를 구성하는 핵심부품이다¹⁾. 전력모듈은 전력반도체 칩(power semiconductor chip), 기판 (substrate), 전기적 연결을 위한 Al 또는 Cu 와이어 (wire), base plate 등으로 구성되며 각 구성 부품들의 접합을 통해 모듈로서 기능을 수행한다. 최근 전력모듈의 사용은 점차 확대되고 있고 순수 전기자동차 (electrical vehicle, EV), 하이브리드 자동차(hybrid electrical vehicle, HEV)와 같은 친환경 자동차에서 사용이 증가하고 있다²⁾. 전력모듈을 구성하는 전력반도체 칩으로는 Si, SiC, GaN 기반의 소자들이 사용되고 있으며³⁾, 기판은 제작방법에 따라 DBC(direct bond copper), AMB(active metal brazing) 등의 세라믹기판의 기판들이 다양한 표면처리를 통하여 사용되고 있다⁴⁾. 이러한 전력반도체 칩과 기판간의 접합은 Pb가 포함된 유연 솔더(solder)를 사용하는 솔더링(soldering) 기술이 그동안 사용되었으나 환경규제로 인해 Pb의 사용이 금지되면서 최근에는 Sn-Ag-Cu, Sn-Zn와 같은 Sn을 기반으로 하는 무연 솔더(Pb-free solder)가 주로 사용되고 있다⁵⁾. 일반적인 자동차에 사용되는 전력모듈은 200 °C 이상의 고온의 환경에 노출되므로 용점이 약 231 °C인 Sn 기반의 무연 솔더를 사용하는 솔더링 방법은 칩과 기판의 접합 후, 전력모듈을 사용할 경우 재용융(re-melting)과 같은 신뢰성 문제가 발생할 수 있는 문제를 가지고 있다⁶⁾. 따라서 이러한 문제를

극복하고자 고온의 환경에서 사용가능한 전력모듈 접합소재 및 접합공정으로 기존 솔더링 방식을 이용하되 높은 용점을 가지는 Au-Sn계 무연 솔더를 사용하는 방법^{7,8)}, Ag 또는 Cu 금속 파우더(powder)를 페이스트 형태로 만들어 소결하는 신터링(sintering) 방법이 연구되고 있다^{9,10)}. 그러나 Au-Sn계 무연 솔더를 사용하는 경우 Au의 높은 가격으로 산업에 적용하기에 어려움이 있다¹¹⁾. 또한 Ag와 같은 금속 파우더를 접합소재로 사용하는 신터링 방법의 경우 미세한 입자일수록 좋은 특성을 얻을 수 있는 장점이 있지만 미세한 입자일수록 재료의 가격이 높은 단점이 있다¹²⁾. 또한 Cu 금속 파우더의 경우 Cu 재료 자체의 산화문제를 해결해야 하는 어려움이 있다^{10,12)}. 따라서, 솔더링과 신터링 접합방법의 단점을 개선하고자 TLP(transient liquid phase) 접합 기술이 최근에 제안되고 있다¹³⁾.

TLP 접합은 고용점의 재료 사이에 접합소재의 역할을 하는 저용점의 삽입금속을 용융시키면서 상대적으로 낮은 온도에서 금속 원자의 확산을 통해 형성되는 금속 간화합물(intermetallic compound; IMC)을 접합부 전체에 형성하면서 접합하는 방법이다¹³⁾. 접합부 전체에 형성된 IMC는 높은 용점을 갖는 특성 때문에 고온의 환경에서도 신뢰성을 확보 할 수 있다. 하지만 TLP 접합의 경우 접합부 전체를 균일한 IMC로 형성시키기 위해서는 긴 공정시간이 필요하다는 점에서 큰 단점으로 지적받고 있다¹¹⁾.

본 연구에서는 접합을 위하여 삽입되는 금속 접합소재에 플라즈마 전처리를 통하여 TLP 접합시간에 따른 TLP 접합부의 IMC 형성과 성장에 대하여 보고하였다. 금속 포일 형태의 Sn 프리폼(preform)을 접합소재로 이용하였으며 프리폼에 Ar 플라즈마 표면처리를

통해 Ar 플라즈마 처리가 TLP 접합부의 계면반응과 IMC 형성 그리고 기계적 특성 등에 미치는 영향을 살펴보고자 하였다.

2. 실험 방법

본 연구에서는 TLP 접합을 위하여 Si 칩이 사용되었으며 기판은 DBC 기판을 이용하였다. Si 칩은 Si wafer 위에 스퍼터링 공정으로 Ti와 Cu를 각각 0.05 μm 와 0.5 μm 를 증착하였다. 그 후 칩의 최종 표면처리를 달리하여 TLP 접합부 특성을 비교하고자 Cu와 Ni를 개별적으로 각각 증착하여 두 가지 형태의 Si wafer를 제작하였다. Cu와 Ni의 최종 증착은 전해도금 방식을 이용하여 각각 10 μm 두께로 증착하였다. Cu와 Ni이 최종 증착된 Si wafer는 4 mm $\times$ 4 mm 크기로 다이싱(dicing) 하여 TLP 접합을 위한 칩으로 사용하였다. 접합에 사용된 기판은 380 μm Al_2O_3 기반의 세라믹 기판에 상/하부 양면에 300 μm Cu가 적층된 구조의 DBC 기판을 이용하였다. 사용된 DBC 기판의 크기는 17.8 mm $\times$ 12.7 mm $\times$ 0.98 mm이었으며 Si 칩과 마찬가지로 표면처리에 따른 접합부의 특성을 비교하고자 수 nm의 OSP(organic solderability preservative)와 약 5 μm 의 Ni(P) 표면처리 두 가지 형태로 제작하여 사용하였다. 한편 TLP 접합을 위한 접합 소재로는 약 40 μm 두께를 가지는 4 mm $\times$ 4 mm 크기의 Sn 프리폼을 사용하였다. 본 연구에서는 Ar 플라즈마 처리가 TLP 접합부에 미치는 영향을 알아보기로 Sn 프리폼 상, 하부 양면의 표면에 Ar 플라즈마 전처리를 진행하였다. Ar 플라즈마 표면처리는 가스유량(gas flow) 100 sccm, 파워(power) 100 W, 진공도 0.5 torr에서 약 10분간 진행되었다. TLP 접합은 DBC 기판위에 Ar 플라즈마 처리된 Sn 프리폼을 올려둔 후 그 위에 칩을 배치하고 진공상태에서 온도와 압력을 제어할 수 있는 챔버를 이용하여 진행되었다. TLP 접합이 된 샘플은 Cu 표면처리된 Si 칩/Sn 프리폼/OSP 표면처리된 DBC (Cu/Sn/Cu) 구조와 Ni 표면처리된 Si 칩/Sn 프리폼/Ni(P) 표면처리된 DBC (Ni/Sn/Ni) 구조의 두 가지 형태로 제작하여 TLP 접합부의 구조에 따른 특성을 비교 평가하였다. 이때 TLP 접합은 진공 챔버내에서 온도 300 $^{\circ}\text{C}$, 1 MPa의 압력을 가하여 진행하였으며 10, 30, 60분의 세 조건으로 접합시간을 달리하여 접합시간에 따른 TLP 접합부에 대한 특성을 함께 비교 평가하고자 하였다. Fig. 1에 Cu/Sn/Cu와 Ni/Sn/Ni TLP 접합 공정 모식도를 나타내었다.

또한 TLP 접합 후 접합부의 구조, 접합시간, Ar 플

Fig. 1 Schematic diagrams of TLP bonding process for (a) Cu/Sn/Cu and (b) Ni/Sn/Ni

라즈마 처리에 따른 계면반응과 형성된 IMC를 분석하기 위해 시편의 단면을 연마한 후, 주사전자현미경(scanning electron microscopy: SEM, Inspect F, FEI, USA)과 EDS(energy-dispersive X-ray spectroscopy) 장비를 사용하여 접합부를 관찰, 분석하였다. 또한 TLP 접합부의 기계적 특성 평가를 위해 접합강도 평가 장비(DAGE-4000, Nordson DAGE, UK)를 사용하여 각 접합조건에 따른 접합강도를 비교 평가하였다. 이때 접합강도 평가는 전단높이 25 μm 에서 전단속도 200 $\mu\text{m/s}$ 조건으로 진행 되었다. 한편, 전단강도 평가 후 파단면에 대하여 SEM과 EDS를 이용하여 단면 분석을 진행하고 접합부의 구조, 접합시간과 Ar 플라즈마 표면처리에 따른 영향을 비교하였다.

3. 실험결과 및 고찰

Fig. 2는 Cu/Sn/Cu TLP 접합 후 단면분석 SEM 결과를 나타낸다. 접합시간 10분에서의 단면분석 결과, 접합부에 형성되는 IMC는 Cu-Sn 계에서 일반적으로 형성된다고 알려진¹³⁾ Cu_6Sn_5 와 Cu_3Sn IMC가 형성됨을 확인 할 수 있었다. 또한 Ar 플라즈마 표면처리를 하지 않은 Sn 프리폼을 사용한 경우에는 접합부에 IMC를 형성한 후 남아 있는 잔여 Sn을 확인 할 수 있었다. 반면, Ar 플라즈마 표면처리를 한 Sn 프리폼이 사용된 접합부는 접합시간 10분부터 접합부 전체에 IMC를 형성함을 확인 할 수 있었다. 접합시간이 30, 60분

Fig. 2 Cross-sectional SEM micrographs of Cu/Sn/Cu joints with various bonding times

으로 증가하는 경우에는 Ar 플라즈마 표면처리 유무에 관계없이 접합부 전체가 IMC화 되는 것을 확인 할 수 있었다. 접합시간과 Ar 플라즈마 처리에 따른 Cu/Sn/Cu TLP 접합부를 형성하고 있는 IMC 종류의 비율을 Fig. 3에 나타내었다. Ar 플라즈마 처리와 관계없이 접합시간이 증가할수록 Cu_6Sn_5 가 차지하는 비율은 감소하였으며 Cu_3Sn 의 비율은 증가 하였다. Cu-Sn 계에서 형성되는 IMC는 Cu와 Sn의 확산반응으로 Cu_6Sn_5 가 먼저 형성된다. 그 후 추가적인 Cu의 확산으로 인해 Cu_6Sn_5 와 Cu 사이에서 Cu_3Sn 이 형성된다고 알려져 있다¹⁴⁾.

Fig. 3 Ratio of IMC formed at Cu/Sn/Cu joints with (Ar(Cu)) and without(Cu) plasma surface treatment

따라서 Cu/Sn/Cu 초기 접합부에서는 Cu_6Sn_5 가 성장하고 접합시간이 증가 할수록 $\text{Cu}_6\text{Sn}_5/\text{Cu}$ 계면에서 Cu_3Sn 이 성장한 것으로 생각된다. 한편 Ar 플라즈마 표면처리한 Sn 프리폼을 사용하여 접합시간 10, 30, 60분을 접합한 경우(Ar(Cu)-10, 30, 60)에는 모든 접합 시간에서 접합부에 Cu_3Sn 가 차지하는 비율이 플라즈마 처리 없이 10, 30, 60분을 접합한 경우 (Cu-10, 30, 60)보다 높았다. 대표적인 비활성 기체인 Ar 가스를 플라즈마 반응가스로 사용할 경우 표면 개질할 시료의 표면과 화학 반응 대신에 물리적인 유기물질 제거와 표면 활성화를 할 수 있는 장점¹⁵⁾을 활용하기 위해 Sn 프리폼에 Ar 플라즈마 표면처리를 적용 하였는바, 이러한 Ar 플라즈마 처리에 의하여 계면에서의 젖음성, 반응성, 접합성 등이 향상되어 TLP 접합부에 균일한 IMC를 형성과 지속적인 Cu의 확산을 가속화하여 Cu_3Sn 의 성장률이 높은 것으로 생각된다.

Fig. 4는 Cu/Sn/Cu TLP 접합부에 대한 플라즈마 표면처리 유무와 접합시간에 따른 접합강도 평가 결과를 나타낸다. 플라즈마 표면처리를 하지 않은 경우 접합시간 10분(Cu-10)은 접합강도가 약 48 MPa로 다른 조건들에 비하여 상대적으로 높은 값을 나타내었다. 접합시간 30분의 접합강도 값은 플라즈마 처리를 하지 않은 경우(Cu-30) 24 MPa 그리고 Ar 플라즈마 표면처리한 경우(Ar(Cu)-30)는 29 MPa 수준으로 측정되었다. 접합시간이 60분으로 증가하면 플라즈마 처리 유무에 관계없이 (Cu-60, Ar(Cu)-60) 강도가 증가하는 경향을 나타내어 접합강도는 각각 25, 34 MPa의 값을 나타내었다. 또한 접합시간 30분 이후에는 플라즈마 처리를 한 경우에 상대적으로 높은 강도를 나타냈다. Cu/Sn/Cu TLP 접합부에 대한 접합강도 평가 후 발생한 파단면의 단면분석 SEM 결과와 이를 바탕으로

Fig. 4 Shear strength of Cu/Sn/Cu joints for various bonding times and Ar plasma treatment

Fig. 5 (a) Cross sectional SEM micrographs of fracture surface and (b) fracture mode of Cu/Sn/Cu joints after shear test

한 파단 모식도를 Fig. 5에 나타내었다. 파단은 접합시간 및 표면처리 유무와 관계없이 접합부의 하단부인 기판과 가까운 쪽에서 발생한 것으로 확인되었다. Fig. 5(a)와 Fig. 5(b) Case 1에서와 같이 플라스마 표면처리를 하지 않은 접합시간 10분의 경우 파단은 접합부에 잔여 Sn과 IMC의 계면, Cu_6Sn_5 와 Cu_3Sn IMC 계면에서 파단이 발생함을 확인할 수 있었다. 앞서 표면처리를 하지 않은 접합시간 10분의 조건에서 상대적으로 높은 강도 값을 나타내었는데 파단면의 단면 분석 결과로 볼 때, 이는 초기 접합부에 IMC를 형성하다 남은 잔여 Sn의 영향으로 일반적인 Sn 기반의 솔더 접합부에서 나타나는 연성특성에 기인한 것으로 생각된다. 이는 접합 공정시간이 초기인 경우 접합부에 잔여 Sn이 남아 있을 때, 접합강도 평가 결과 높은 접합강도 값을 나타내는 이전의 연구결과와 유사한 경향을 확인 하였다¹³⁾. 한편 Ar 플라스마 표면처리를 한 접합시간 10분의 접합부 경우에는 Fig. 5(a)와 Fig. 5(b) Case 2 같이 Cu_6Sn_5 와 Cu_3Sn 의 계면에서 파괴가 발생함을 확인할 수 있었다. 이는 Ar 플라스마 표면처리를 한 경우 접합시간 10분부터 접합부 전체에 IMC를 형성하기 때문에 Ar 플라스마 처리를 하지 않은 경우와 다르게 나타난 것으로 생각되며 IMC 계면에서 파괴로 인하여 접합시간 10분의 접합강도는 상대적으로 Ar 플라스마 표면처리를 하지 않은 경우보다 낮게 나타난 것으로 보인다. 접합시간이 30, 60분으로 증가하는 경우 접합부의 파

괴는 Fig. 5(a)와 Fig 5(b)의 Case 3, 4와 같이 Ar 플라스마 처리 유무에 관계없이 Cu_6Sn_5 IMC 층 내부 및 Cu_6Sn_5 와 Cu_3Sn 의 계면에서 발생하는 것을 확인할 수 있었다. 앞서 Fig. 3에서 언급한 바와 같이 접합시간이 증가하면서 접합부의 Cu_3Sn IMC의 비율이 증가하였는데 이는 접합시간 30분 이후에 파단의 경로는 유사함에도 불구하고 접합시간이 증가하면서 강도가 증가하는 것은 Cu_3Sn IMC가 접합부에 차지하는 비중의 증가가 영향을 미친 것으로 생각된다. 일반적으로 Cu_6Sn_5 보다 Cu_3Sn 이 일반적으로 Young's Modulus 등이 높게 나타나는데¹⁶⁾ 본 연구에서 접합시간이 증가하고 Ar 플라스마 표면처리를 할 경우 상대적으로 Cu_3Sn 의 비율이 증가하는 것으로 나타난 바, 이러한 Cu_3Sn 의 증가가 TLP 접합부의 강도 증가에 영향을 미친 것으로 생각된다.

Fig. 6은 Ni/Sn/Ni TLP 접합 후 단면분석 SEM 결과를 나타낸다. 접합부에 형성된 IMC는 Ni_3Sn_4 로 확인되었으며 접합시간 10분에서는 Ar 플라스마 표면처리를 하지 않은 경우 Cu/Sn/Cu 접합부와 마찬가지로 잔여 Sn이 접합부 중앙에서 확인할 수 있었다. 반면, Ar 플라스마 표면처리한 Sn 프리폼을 사용한 경우 접합부 전체에 IMC가 형성됨을 확인할 수 있었다. 일반적으로 Ni-Sn 계는 Ni_3Sn_4 IMC가 형성된다고 알려졌다¹³⁾, Sn 계 솔더와 무전해 Ni(P) 도금된 계면에서는 Ni-Sn-P와 Ni_3P 가 형성된다고 알려져 있다¹⁷⁻²⁰⁾. 본 연구에서는 이전의 연구들과 유사하게 Ni(P) 표면처

Fig. 6 Cross-sectional SEM micrographs of Ni/Sn/Ni joints with various bonding times

리된 DBC기판과 Sn 프리폼의 계면에서 Ni-Sn-P와 Ni₃P가 형성됨을 확인 하였다. 한편 접합시간이 30, 60 분으로 증가하면서 Ar 플라즈마 표면처리를 하지 않은 경우에도 접합부 전체는 Ni₃Sn₄ IMC가 형성되었다. Ar 플라즈마 표면처리 유무와 접합시간에 따른 접합부에 형성된 IMC들이 접합부를 차지하는 비율을 Fig. 7에 나타냈다. 접합시간 10분은 Ar 플라즈마 표면처리가 없는 경우(Ni-10)에는 접합부에 IMC로 형성하지 못한 잔여 Sn의 영향으로 접합부에서 Ni₃Sn₄ IMC가 차지하는 비율이 가장 낮았다. 그러나 접합시간이 30,

Fig. 7 Ratio of IMC formed at Ni/Sn/Ni joints with (Ar(Ni)) and without(Ni) plasma surface treatment

60분(Ni-30, Ni-60)으로 증가하면서 남아 있는 Sn이 반응하여 Ni₃Sn₄와 Ni-Sn-P, Ni₃P의 비율이 증가함을 확인할 수 있었다. Ni-Sn-P와 Ni₃P의 경우 접합부 전체에 Ni₃Sn₄ IMC가 형성한 후에는 시간에 따라 일부 증가하기는 하나 두드러지게 증가하지는 않는 것으로 확인되었다. 또한 Ar 플라즈마 처리를 한 접합부의 경우에는 접합시간 10분 (Ni(Ar)-10)부터 접합부 전체에 Ni₃Sn₄ IMC가 형성됨에 따라 접합시간이 30, 60분(Ni(Ar)-30, Ni(Ar)-60)으로 증가하더라도 접합부를 형성하는 IMC들의 비율은 큰 차이를 나타내지 않았다.

Fig. 8은 Ni/Sn/Ni TLP 접합부의 접합강도 결과로 Cu/Sn/Cu TLP 접합부에 대한 접합강도 평가 결과와 유사한 경향을 확인 하였다. Ar 플라즈마 표면처리 하지 않은 Sn 프리폼을 사용한 접합시간 10분(Ni-10) 접합부의 경우 접합부에 잔여 Sn의 영향으로 43 MPa의 높은 강도를 나타내었다. 이는 Cu/Sn/Cu TLP 접합부에서 설명한 바와 같이 남아 있는 Sn의 연성 특성으로 인한 것으로 생각된다. 그러나 접합시간이 30, 60분(Ni-30, Ni-60)으로 증가하면서 Ni₃Sn₄가 접합부 전체에 형성된 후에는 접합강도가 23-25 MPa 수준으로 접합시간에 따라 큰 차이를 나타내지는 않았다. 한편 Ar 플라즈마 표면처리를 한 경우와 같이 접합시간 10분(Ni(Ar)-10)부터 접합부에 Ni₃Sn₄ IMC가 접합부 전체에 IMC가 형성될 때에는 접합시간이 30, 60분(Ni(Ar)-30, Ni(Ar)-60)으로 증가하더라도 접합시간에 따른 접합강도는 초기 10분부터 유사한 값을 나타냄을 확인할 수 있었다. 따라서, Ni/Sn/Ni 구조에서 Ni₃Sn₄ IMC가 접합부 전체에 형성된 경우 Ar 플라즈마 표면처리 유무와 접합시간은 접합강도에 크게 영향을 미치지 않는 것으로 생각된다. 접합시간과 플라

Fig. 8 Shear strength of Ni/Sn/Ni joints for various bonding times and Ar plasma treatment

Fig. 9 (a) Cross sectional SEM micrographs of fracture surface and (b) fracture mode of Ni/Sn/Ni joints after shear test

즈마 표면처리 유무에 따라 Ni/Sn/Ni TLP 접합부의 파단면 단면분석 결과와 파단 발생 모드도를 Fig. 9에 나타냈다. 접합부의 파괴는 Cu/Sn/Cu TLP 접합부와 유사하게 대부분 기관과 가까운 접합부의 하단에서 발생하였다. 접합시간 10분에서 플라즈마 처리가 되지 않은 경우 잔여 Sn이 남아있는 접합부에 남아있을 때 Fig. 9(a)와 (b)의 Case 1과 같이 파단경로가 Ni_3Sn_4 IMC와 잔여 Sn 계면에서 파단이 발생하였다. 그러나 접합시간이 30, 60분으로 증가한 경우 접합부 전체에 Ni_3Sn_4 IMC를 형성함에 따라 파괴는 Ni_3Sn_4 IMC, Ni_3Sn_4 와 Ni-Sn-P의 계면에서 발생함을 확인 할 수 있었다. 반면, Ar 플라즈마 처리를 한 경우에는 Fig. 9(a)와 (b)의 Case 2에서와 같이 접합시간 10분부터 Ni_3Sn_4 IMC, Ni_3Sn_4 와 Ni-Sn-P의 계면에서 발생하였다. 이러한 파괴모드의 유사성으로 인하여 Ar 플라즈마가 처리되지 않은 접합시간 30분(Ni-30) 이후의 접합부와 Ar 플라즈마가 처리된 접합시간 10분(Ar(Ni)-10) 이후의 접합부에서 유사한 접합강도가 나타난 것으로 생각된다.

4. 결 론

본 연구에서는 전력모듈을 위한 TLP 접합공정의 시간을 단축하기 위한 방법으로, 접합소재로 사용된 Sn 프리폼 삽입금속 표면에 Ar 플라즈마 표면처리를 하여 Ar 플라즈마 처리가 TLP 접합부의 계면반응과 기계적

특성에 미치는 영향을 살펴보았다. 또한 Cu/Sn/Cu와 Ni/Sn/Ni 구조의 TLP 접합부를 형성하여 Ar 플라즈마 표면처리, TLP 접합부 구조, TLP 접합시간 등의 TLP 접합조건에 따른 접합부의 특성에 대하여 연구하였다.

1) Sn 프리폼에 Ar 플라즈마 처리를 한 경우 접합시간 10분으로도 Cu/Sn/Cu와 Ni/Sn/Ni 구조의 TLP 접합부에서 접합부 전체를 IMC로 형성할 수 있었다. 이는 Ar 플라즈마 처리가 물리적인 세정 효과 등의 영향으로 Cu, Ni, Sn 등의 금속원자의 확산에 영향을 미친 것으로 생각된다.

2) Ar 플라즈마 처리를 하지 않은 경우에는 접합시간 10분에서 Cu/Sn/Cu와 Ni/Sn/Ni 구조 접합부 모두 접합부 전체에 IMC를 형성하지 못하고 남은 Sn이 확인 되었다.

3) Cu/Sn/Cu TLP 접합부에서는 Cu_6Sn_5 와 Cu_3Sn IMC가 형성 되었으며 Ni/Sn/Ni TLP 접합부에서 Ni_3Sn_4 , Ni-Sn-P, Ni_3P IMC가 형성됨을 확인 하였다.

4) Cu/Sn/Cu 접합부에서는 접합시간이 증가함에 따라 Cu_3Sn IMC가 접합부를 차지하는 비율이 증가하였고 Cu_3Sn 비율이 증가함에 따라 접합부의 강도는 증가하였다.

5) Ni/Sn/Ni 접합부에서는 접합부 전체에 Ni_3Sn_4 IMC가 형성된 경우에는 Ar 표면처리 및 접합시간은 접합강도에 크게 영향을 미치지 않은 것으로 판단된다.

6) 본 연구결과 TLP 접합에 접합소재로 사용되는 삽입금속 형태의 프리폼을 이용할 경우 프리폼에 Ar 전처리는 TLP 접합부 전체를 빠르게 IMC로 형성할 수 있어 공정 시간을 단축시킬 수 있을 것으로 기대된다.

감사의 글

본 논문은 한국생산기술연구원 기관주요사업 “제품생산 유연성 확보를 위한 뿌리공정기술 개발(kitech EO-20-0015)”의 지원으로 수행한 연구입니다.

ORCID: Seungju Baek: <https://orcid.org/0000-0003-0746-7378>

ORCID: Yong-Ho Ko: <https://orcid.org/0000-0002-1619-8467>

References

1. M. Thoben, F. Sauerland, K. Mainka, S. Edenharter and L. Beaurenaut, Lifetime modeling and simulation of power modules for hybrid electrical/electrical vehicles, *Microelectron. Reliab.* 54 (2014) 1806-1812. <https://doi.org/10.1016/j.microrel.2014.07.009>
2. Y. Wang, S. Jones, A. Dai and G. Liu, Reliability enhancement by integrated liquid cooling in power IGBT modules for hybrid and electric vehicles, *Microelectron. Reliab.* 54 (2014) 1911-1915. <https://doi.org/10.1016/j.microrel.2014.07.037>
3. L. A. Navarro, X. Perpiñà, P. Godignon, J. Montserrat, V. Banu, M. Vellvehi and X. Jordà, Thermomechanical assessment of die-attach materials for wide bandgap semiconductor devices and harsh environment applications, *IEEE Trans. Power Electron.* 29(5) (2014) 2261-2271. <https://doi.org/10.1109/TPEL.2013.2279607>
4. H. A. Mantooth, S. S. Ang, B. L. Rowden and J. C. Balda, Packaging of High-Temperature Power Semiconductor Modules, *ECS Trans.* 27(1) (2010) 909-914. <https://doi.org/10.1149/1.3360729>
5. K. Suganuma, Advances in lead-free electronics soldering, *Curr. Opin. Solid State Mater. Sci.* 5(1) (2001), 55-64. [https://doi.org/10.1016/S1359-0286\(00\)00036-X](https://doi.org/10.1016/S1359-0286(00)00036-X)
6. H. Zhang, S. S. Ang, H. A. Mantooth and S. Krishnamurthy, A high temperature, double-sided cooling SiC power electronics module, *IEEE Energy Convers. Congr. Expo. (ECCE)* (2013) 2877-2883. <https://doi.org/10.1109/ECCE.2013.6647075>
7. D. G. Ivey, Microstructural characterization of Au/Sn solder for packaging in optoelectronic applications, *Micron.* 29(4) (1998) 281-287. [https://doi.org/10.1016/S0959-4328\(97\)00057-7](https://doi.org/10.1016/S0959-4328(97)00057-7)
8. J. W. Yoon, H. S. Chun and S. B. Jung, Liquid-state and solid-state interfacial reactions of fluxless-bonded Au-20Sn/ENIG solder joint, *J. Alloys Compd.* 469 (2009) 108-115. <https://doi.org/10.1016/j.jallcom.2008.01.077>
9. B. S. Lee and J. W. Yoon, Die-Attach for Power Devices Using the Ag Sintering Process, Interfacial Microstructure and Mechanical Strength, *Met. Mater. Int.* 23 (2017) 958-963. <https://doi.org/10.1007/s12540-017-6908-1>
10. J. W. Yoon, J. H. Back and S. B. Jung, Effect of surface finish metallization on mechanical strength of Ag sintered joint, *Microelectron. Eng.* 198 (2018) 15-21. <https://doi.org/10.1016/j.mee.2018.06.009>
11. S. Sohn, B. Moon, J. Lee, N. Kang and Y. Moon, Interlayer Material Design Reducing Transient Liquid Phase Bonding Time, *Electron. Mater.* 16(2) (2020) 106-114. <https://doi.org/10.1007/s13391-019-00191-2>
12. J. W. Yoon, S. Bae, B. S. Lee and S. B. Jung, Bonding of power device to ceramic substrate using Sn-coated Cu micro paste for high-temperature applications, *Appl. Surf. Sci.* 515 (2020). <https://doi.org/10.1016/j.apsusc.2020.146060>
13. B. S. Lee, S. K. Hyun and J. W. Yoon, Cu-Sn and Ni-Sn transient liquid phase bonding for die-attach technology applications in high-temperature power electronics packaging, *J. Mater. Electron.* 28(11) (2017) 7827-7833. <https://doi.org/10.1007/s10854-017-6479-4>
14. X. Liang, X. Li, P. Yao, Y. Li and F. Jin, Interfacial reaction during fabricating of full Cu₃Sn joints in micro-electronic packaging, *Mater. Sci. Tech.* 33(17) (2017) 2024-2031. <https://doi.org/10.1080/02670836.2017.1342365>
15. J. Wang, Q. Wang, D. Wang and J. Cai, Study on Ar(5%H₂) Plasma Pretreatment for Cu/Sn/Cu Solid-State-Diffusion Bonding in 3D Interconnection, *Proceedings Electronic Components and Technology Conference (ECTC)*, Las Vegas, NV, USA (2016) 1765-1771. <https://doi.org/10.1109/ECTC.2016.110>
16. C. C. Lee, P. J. Wang and J. S. Kim, Are intermetallics in solder joints really brittle?, *Proceedings Electronic Components and Technology Conference (ECTC)*, Reno, NV, USA (2007) 648-652. <https://doi.org/10.1109/ECTC.2007.373866>
17. J. W. Yoon and S. B. Jung, Growth kinetics of Ni₃Sn₄ and Ni₃P layer between Sn-3.5Ag solder and electroless Ni-P substrate, *J. Alloys Compd.* 376 (2004) 105-110. <https://doi.org/10.1016/j.jallcom.2003.12.029>
18. H. Lee, S. H. hun, G. H. Jung, and S. J. Ham, Effects of the Electroless Ni-P Thickness and Assembly Process on Solder Ball Joint Reliability, *J. Weld. Join.* 32(4) (2014) 60-67. <https://doi.org/10.5781/JWJ.2014.32.3.60>
19. J. W. Yoon and S. B. Jung, Coupling effect of Cu(ENIG)/Sn-Ag-(Cu)/Cu(ENIG) sandwich solder joint, *J. Weld. Join.* 46 (2006) 33-35.
20. J. H. Back, S. Yoo, D. G. Han, S. B. Jung, and J. W. Yoon, Interfacial Reactions and Mechanical Strength of Sn-3.0Ag-0.5Cu/0.1μm-Ni Thin ENEPIG Solder Joints, *J. Weld. Join.* 35(6) (2017) 51-58. <https://doi.org/10.5781/JWJ.2017.35.6.8>